
$\label{lem:contact: Add: No. 2000 Shunhua Rd, High-Tech Zone , Jinan City, Shandong Province, China Contact: +86-18653132120 Website: www.unilongmaterial.com$

Product name: Hexadecanethiol

CAS: 2917-26-2

Molecular wight:258.51



Item	Standard
Melting point	18-20 °C(lit.)
Boiling point	184-191 °C7 mm Hg(lit.)
Density	0.84 g/mL at 25 °C(lit.)
Vapor pressure	<0.1 hPa (20 °C)
Refractive index	n20/D 1.462(lit.)
Flash point	215 °F

Add: No.2000 Shunhua Rd, High-Tech Zone , Jinan City, Shandong Province, China Contact: +86-18653132120 Website:www.unilongmaterial.com

Application:

Hexadecanethiol is used for electroplating and its chemical additives. In addition, Hexadecanethiol is also an important intermediate and raw material for the synthesis of fine and pharmaceutical sulfur-containing products.

Package:

25kg/drum or according to customers requirements.